

Purity Improves Process

Metallic Resources' SAC0807 lead free solder alloy is manufactured from electrolytically processed tin and other elements to create solder so pure it far exceeds the most common specifications. It has been independently tested to meet all restrictions on hazardous substances. It is RoHS compliant. The specific alloy is Sn98.5/Ag0.8/Cu0.7. Standard packaging is 25-pound boxes containing cast bars. Also available are nuggets, ingots, or feeder bars.

Versatile & Reliable

Metallic Resources' high purity SAC0807 electrolytic alloy has been specially formulated and designed for use in all wave soldering, and tin and dip soldering applications. It is ideally suited for the assembly of printed circuit boards utilizing existing or new equipment found in the electronics market.

Higher Yield, Less Waste

Manufactured using an electrolytic process, Metallic Resources' SAC0807 lead free solder is lower in viscosity, which improves the fluidity. Greater fluidity improves the solder's wetting capability for better through hole fill, and reduces necessary re-work including bridging, icicling, cobwebbing and flagging. High purity electrolytic solder is environmentally friendly, and generates less dross compared to other "virgin grade" lead free alloys. Less dross results in a greater number of joints per pound of solder consumed and greater cost effectiveness. Energy savings, extended pot life, reduced thermal stress, and reduced potential of contamination are all benefits derived from the electrolytic manufacturing process. The electrolytic manufacturing process assures batch-to-batch consistency for predictable performance in the solder pot. The process removes most metallic and non-metallic impurities often found in "virgin metals" to provide a purer solder alloy. This purity results in a smaller crystalline structure which exhibits a shinier, more brilliant solder appearance when compared to other SAC0807 alloys.

Exceeds Industry Standards

Lead Free SAC0807 bar solder conforms to the requirements of IPC Specification J-STD-006. It meets or exceeds ASTM-32, and is approved for military usage. It complies with Directive 2011/65/EU and Directive 2015/863/EU Restriction of Hazardous Substances (RoHS 2 and 3). Certificates of Conformance and Analysis are automatically provided with each shipment.



Metallic Resources, Inc.



Ph: 330.425.3155 | Fax: 330.425.2180

2368 E. Enterprise Parkway | Twinsburg, OH 44087

Physical Properties

Melting Point	225°C
Density	7.4 g/cm ³
Operating Temperature	255-265°C
Tensile Strength	30.7 M Pa
Tensile Elongation	21%
Thermal Conductivity	64 J/m ² •K
Electrical Resistivity	0.000014 Ohm-cm
Thermal Shock -10 to +100°C	> 1000 cycles

Technical Specifications		
	SAC0807 MRI Specification	J-STD-006 Alloy Specification
Sn	98.500 ± 0.5	98.500 ± 0.5
As	.0035 (max)	.0300 (max)
Sb	.0250 (max)	.2000 (max)
Au	.0020 (max)	.0500 (max)
Fe	.0050 (max)	.0200 (max)
Ni	.0060 (max)	.0100 (max)
Bi	.0100 (max)	.1000 (max)
Al	.0010 (max)	.0050 (max)
Cu	.7000 ± 0.1	.7000 ± 0.1
Ag	.8000 ± 0.1	.8000 ± 0.1
Zn	.0010 (max)	.0030 (max)
Cd	.0010 (max)	.0020 (max)
In	.0100 (max)	.1000 (max)
Pb	.0500 (max)	.0700 (max)

Metallic Resources, Inc.

Ph: 330.425.3155 | Fax: 330.425.2180
2368 E. Enterprise Parkway | Twinsburg, OH 44087

SAC0807-0927

Recommendations made by this company and its representatives are based upon test data, experiments, and experience believed to be reliable. No guarantee of accuracy is made, however. All products are sold upon the condition that the buyer will make his own tests and assume the responsibility for the suitability of the product under his application and service conditions. Statements made herein will vary according to the nature of the surfaces to which the product is applied, application technique, and service condition. We in no event assume liability beyond the purchase price of our products involved and make as a condition of Sale that we will refund the purchase price or replace materials proven to be defective and reported in a timely fashion, but no later than six (6) months after shipment. No representative of the manufacturer and/or seller has the authority to alter or extend these conditions.